

TEST SPECIMEN AND COMPRESSIVE STRENGTH DATA SHEET

PROJECT AND CAST DATA (PERFORMED BY OTHERS AND NOT VERIFIED BY LAB)

Project Name:

NR

Inspector's License Number:

On File

Job Address:

449 Park Avenue #B
San Fernando, CA

Permit No:

NR

Inspection Firm or Client:

Bellecrete Inc.

Inspector's Name:

NR

Contractor:

NR

Field Identification:

NR

Cast Date:

04/27/2024

Description:

Concrete Cylinders 4x8

Cement Type:

NR

Concrete Supplier:

NR

Specified F'c - PSI:

For Information Only

Admixture:

NR

Plant:

NR

Cast By:

NR

Slump (C143):

0 in

Mix Design No:

NR

No of Samples:

2

Air Content (C173) (C231):

NR

Ticket Number:

NR

Total Yards:

NR

Air Temp (C1064):

0F

Cast / Mix Time:

NR

Concrete Temp (C1064):

0F

Location:

NR

Notes:

NR

NR = Not Reported. Results relate only to the tested specimens.

LABORATORY COMPRESSIVE STRENGTH DATA PER ASTM C1231 (Unbonded Method)

Date Specimens Received:

05/06/2024

Equipment Used:

On File

Report Date:

05/25/2024

SN of Equipment:

On File

Technician Name:

Michael Ahdunko

Calib. / Recal. Date

On File

| Test Data | | | | | | | | | | | |
|-----------------------|----------------|-----------------|-----------------|-----------------------------------------|--------|--------|--------|-------------------------|--------------|------------|----------------------------|
| Specimen ID Number | Age at Test | Date Of Test | Time Of Test | Specimen Dimensions (in. ²) | | | | Area In ² | Load Lbs. | F'c PSI | Break Type ³ |
| | | | | 1 (in) | 2 (in) | 3 (in) | 4 (in) | | | | |
| 123813.1.1 | 9 | 05/06/2024 | 1:23 PM | 4.00 | 4.01 | NA | NA | 12.60 | 59,140 | 4,690 | 2 |
| 123813.1.2 | 28 | 05/25/2024 | 8:03 AM | 4.00 | 4.00 | NA | NA | 12.57 | 74,210 | 5,900 | 2 |
| 28-DAY Avg. F'c PSI: | | | | | | | | | | 5,900 | |

¹ Test Schedule Provided by the Client

² Dimensions 1 and 2 = Diameters; Dimensions 3 and 4 = Height; NA if Cylinder 2.2 > l/d > 1.8

³ Break Type Designation DATA PER ASTM C1231 (Unbonded Method) Figure 2: 1 = Cone, 2 = Cone and Crack, 3 = Columnar, 4 = Diagonal, 5 = Side Fracture, 6 = Side Fracture Point

THE TEST RESULTS ARE FOR INFORMATION ONLY

V. Benitez

Authorized Signature