Materials Testing Since 1989

SPECIALIZED TESTING

Committed to a Safer World

ISO 17025 Accredited

TEST SPECIMEN AND COMPRESSIVE STRENGTH DATA SHEET

PROJECT AND CAST DATA (PERFORMED BY OTHERS AND NOT VERIFIED BY LAB)

Project Name:	NR	**Inspection Firm or Client:**	Bellecrete Inc.
Inspector's License Number:	On File	**Inspector's Name:**	NR
Job Address:	449 Park Avenue #B San Fernando, CA	**Contractor:**	NR
Permit No:	NR	**Field Identification:**	NR

Cast Date:	04/30/2024	**Description:**	**Concrete Cylinders 4x8**	**Cement Type:**	NR
Concrete Supplier:	NR	**Specified F'c - PSI:**	For Information Only	**Admixture:**	NR
Plant:	NR	**Cast By:**	NR	**Slump (C143):**	0 in
Mix Design No:	NR	**No of Samples:**	2	**Air Content (C173) (C231):**	NR
Ticket Number:	NR	**Total Yards:**	NR	**Air Temp (C1064):**	0F
Cast / Mix Time:	NR	**Concrete Temp (C1064):**	0F		
Location:	NR				
Notes:	NR				

NR = Not Reported. Results relate only to the tested specimens.

LABORATORY COMPRESSIVE STRENGTH DATA PER ASTM C1231 (Unbonded Method)

Date Specimens Received:	05/06/2024	**Equipment Used:**	On File
Report Date:	05/28/2024	**SN of Equipment:**	On File
Technician Name:	Michael Ahdunko	**Calib. / Recal. Date**	On File

Test Data

Specimen ID Number	Age at Test	Date Of Test	Time Of Test	Specimen Dimensions (in.^{2})				Area In^2	Load Lbs.	F'c PSI	Break Type[3]
				1 (in)	2 (in)	3 (in)	4 (in)				
123813.3.1	6	05/06/2024	1:26 PM	4.00	4.01	NA	NA	12.60	69,200	**5,490**	3
123813.3.2	28	05/28/2024	10:00 AM	4.00	4.01	NA	NA	12.60	78,120	**6,200**	3
									28-DAY Avg. F'c PSI:	**6,200**	

[1] Test Schedule Provided by the Client

[2] Dimensions 1 and 2 = Diameters; Dimensions 3 and 4 = Height; NA if Cylinder 2.2 > l/d > 1.8

[3] Break Type Designation DATA PER ASTM C1231 (Unbonded Method) Figure 2: 1 = Cone, 2 = Cone and Crack, 3 = Columnar, 4 = Diagonal, 5 = Side Fracture, 6 = Side Fracture Point

THE TEST RESULTS ARE FOR INFORMATION ONLY

V. Benitez

Authorized Signature